



# Microfabricated Chemical Sensors for Safety and Emission Control Applications

G.W. Hunter, P.G. Neudeck, and L.-Y. Chen  
Lewis Research Center, Cleveland, Ohio

D. Knight  
Cortez III Service Corporation, Cleveland, Ohio

C.C. Liu and Q.H. Wu  
Case Western Reserve University, Cleveland, Ohio

## The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized data bases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to [help@sti.nasa.gov](mailto:help@sti.nasa.gov)
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:  
NASA Access Help Desk  
NASA Center for AeroSpace Information  
7121 Standard Drive  
Hanover, MD 21076



# Microfabricated Chemical Sensors for Safety and Emission Control Applications

G.W. Hunter, P.G. Neudeck, and L.-Y. Chen  
Lewis Research Center, Cleveland, Ohio

D. Knight  
Cortez III Service Corporation, Cleveland, Ohio

C.C. Liu and Q.H. Wu  
Case Western Reserve University, Cleveland, Ohio

Prepared for the  
17th Digital Avionics Systems Conference  
cosponsored by the American Institute of Aeronautics and Astronautics  
and the Institute of Electrical and Electronics Engineers  
Bellevue, Washington, October 31—November 6, 1998

National Aeronautics and  
Space Administration

Lewis Research Center

## Acknowledgments

The authors would like to acknowledge the contributions of Dr. J. Lei, Dr. H. Will, and Dr. D. Larkin of NASA LeRC, Dr. D. Makel of Makel Engineering, and the technical assistance of D. Androjna and C. Salupo of Cortez/NASA LeRC. L. Chen is a NRC Fellow.

### Available from

NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076  
Price Code: A03

National Technical Information Service  
5285 Port Royal Road  
Springfield, VA 22100  
Price Code: A03

# Microfabricated Chemical Sensors for Safety and Emission Control Applications

*Gary W. Hunter, Philip G. Neudeck, and Liang-Yu Chen\**

*National Aeronautics and Space Administration*

*Lewis Research Center*

*Cleveland, Ohio USA 44135*

*Dak Knight*

*Cortez III Service Corporation*

*Cleveland, Ohio USA 44135*

*C. C. Liu and Q. H. Wu*

*Case Western Reserve University*

*Electronics Design Center*

*Cleveland, Ohio USA 44106*

## ABSTRACT

Chemical sensor technology is being developed for leak detection, emission monitoring, and fire safety applications. The development of these sensors is based on progress in two types of technology: 1) Micromachining and microfabrication (MEMS-based) technology to fabricate miniaturized sensors. 2) The development of high temperature semiconductors, especially silicon carbide. Using these technologies, sensors to measure hydrogen, hydrocarbons, nitrogen oxides, carbon monoxide, oxygen, and carbon dioxide are being developed. A description is given of each sensor type and its present stage of development. It is concluded that microfabricated sensor technology has significant potential for use in a range of aerospace applications.

## INTRODUCTION

Aerospace applications require the development of chemical sensors with capabilities beyond those of commercially available sensors.

Three areas of particular interest are leak detection, emission monitoring, and fire detection. In launch vehicle safety applications, the detection of hydrogen leaks is important for applications involved with, for example, operation of the Space Shuttle. In 1990, the leaks on the Space Shuttle while on the launch pad temporarily grounded the fleet until the leak source could be identified. In response to the hydrogen leak problems, NASA endeavored to improve propellant leak detection capabilities during assembly, pre-launch operations, and flight. In particular, efforts were made to develop an automated hydrogen leak detection system using point-contact hydrogen sensors. However, no commercial sensors existed at that time that operated satisfactorily in this and other space related applications. For example, commercially available sensors often needed oxygen or depended upon moisture to operate.<sup>1</sup> Such sensors did not meet the needs of this application where hydrogen detection was necessary in inert environments or upon exposure to cryogenic environments.<sup>2</sup> Thus the development of new types of sensors was necessary.

---

\* National Research Council Research Associate.

The development of a new class of sensors is also necessary for the monitoring of emissions from aircraft engines. The control of emissions from aircraft engines is an important component of the development of the next generation of these engines. The ability to monitor the type and quantity of emissions being generated by an engine is important in not only controlling those emissions but also in determining the status of the engine. Ideally, an array of sensors placed in the emission stream close to the engine could provide information on the gases being emitted by the engine. However, there are very few sensors available commercially which are able to measure the components of the emissions of an engine in-situ. The harsh conditions and high temperatures inherent near the reaction chamber of the engine render most sensors inoperable.

In fire safety applications, fire detection equipment presently used in the cargo holds of many commercial aircraft relies on the detection of smoke. Although highly developed, these sensors are subject to false alarms. These false alarms may be caused by a number of sources including: changes in humidity, condensation on the fire detector surface, contamination from animals, plants, or other contents of the cargo bay.<sup>3</sup> A second method of fire detection to complement existing techniques, such as the measurement of chemical species indicative of a fire, will help reduce false alarms and improve aircraft safety. Although, many chemical species are indicative of a fire, two species of interest are carbon monoxide and carbon dioxide.<sup>4</sup>

In order to meet the needs of these applications, a new generation of sensor technology must be developed. This paper discusses point-contact sensor technology being developed to address these needs. The development of these sensors is based on progress in two types of technology: 1) Micromachining and microfabrication technology (MEMS-based

technology) to fabricate miniaturized sensors, and 2) The development of high temperature semiconductors, especially silicon carbide, to provide electrical components and sensors operable at the temperatures of interest. Using these technologies, point-contact sensors are being developed to measure hydrogen ( $H_2$ ), hydrocarbons ( $C_xH_y$ ), nitrogen oxides ( $NO_x$ ), carbon monoxide (CO), carbon dioxide ( $CO_2$ ) and oxygen ( $O_2$ ). A description is given of each sensor type and its present stage of development. The silicon (Si) based hydrogen sensor is at a relatively mature stage of development while the state of development of the other sensors ranges from the proof of concept level to prototype stage. The number of dual-use commercial applications makes this general area of sensor development a field of significant interest.

## SENSOR DEVELOPMENT


### *Hydrogen Sensor Technology*

One component of the sensor development program at NASA Lewis Research Center (LeRC) and Case Western Reserve University (CWRU) involves the development of palladium (Pd) alloy Schottky diodes on silicon (Si) substrates. A Schottky diode is composed of a metal in contact with a semiconductor (MS) or a metal in contact with a very thin insulator on a semiconductor (MIS). For gas sensing applications, the metal is often a catalytic film. The advantage of a Schottky diode sensing structure in gas sensing applications is its high sensitivity: factors of over 1000 change in reverse current for 0.5%  $H_2$ .<sup>5</sup> Further, this type of sensor does not need oxygen for operation.

The sensor structure is shown in Figure 1. The structure includes a Pd alloy Schottky diode, a temperature detector, and a heater all incorporated in the same chip. The sensor is fabricated using a n-type silicon wafer on which approximately 50 Å of  $SiO_2$  is

thermally grown in the sensor region. The heater and temperature detector are platinum resistors. Gold leads are applied by thermal compression bonding and the sensor is mounted on a TO5 header or on a ceramic flat package. The surface area of the Schottky diode is  $6.1 \times 10^{-3} \text{ cm}^2$  and the sensor dimensions are approximately 2.2 mm on a side. The response of the Schottky diodes was determined by measuring the diode's reverse current.

A hydrogen sensor using palladium chrome (PdCr) as the  $\text{H}_2$  sensitive alloy is presently under development for use on the NASA experimental vehicle, the X-33, in its hydrogen leak detection system.<sup>6</sup> Palladium chrome was chosen due its ability to detect  $\text{H}_2$  up to 100%. A resistor, whose resistance is dependent on the  $\text{H}_2$  concentration, has been added to the sensor design to expand the detection range of the sensor (Figure 1); a Schottky diode provides sensitive detection of low concentrations of  $\text{H}_2$  while the resistor (also made of PdCr) provides sensitivity up to 100%  $\text{H}_2$ . A complete system with hardware and software included with the sensor is included on the X-33 safety system. This complete system is also scheduled for a demonstration flight on the Shuttle for the fall of 1998.<sup>6</sup>



**Figure 1. Schematic diagram of the Schottky Diode Hydrogen Sensor.** The Pd alloy Schottky diode resides symmetrically on either side of a heater and temperature detector. The resistor expands the sensitivity range of the sensor package to 100% hydrogen.

## Hydrocarbon Detection

The development of hydrocarbon sensors for use in harsh environments has centered on the development of a stable SiC-based Schottky diode. The advantage of SiC over Si is its ability to operate as a semiconductor at temperatures in excess of  $600^\circ\text{C}$ . This allows SiC-based gas sensors to operate at temperature high enough to allow the detection of hydrocarbons.<sup>7</sup> The first Schottky diode structure developed at NASA LeRC was Pd on SiC MS structures (Pd/SiC). Direct contact between the catalytic metal and the semiconductor allows changes in the catalytic metal to have maximum effect on the semiconductor. Studies of this baseline system help determine limits of diode sensitivity, potential material interactions between Pd and SiC, and whether a barrier layer between the Pd and SiC is necessary for long-term sensor stability. The sensor detects  $\text{C}_x\text{H}_y$  in inert or oxygen containing environments. The details of this work are reviewed elsewhere.<sup>7</sup>

Figure 2 illustrates the advantage of SiC over Si in  $\text{C}_x\text{H}_y$  sensing applications. Shown is the zero bias capacitive response of a Pd/SiC Schottky diode to one hydrocarbon (propylene) over a range of temperatures. The sensor temperature is increased from  $100^\circ\text{C}$  to  $400^\circ\text{C}$  in steps of  $100^\circ\text{C}$  and the response of the sensor is observed. At a given temperature, the sensor is exposed to air for 20 minutes,  $\text{N}_2$  for 20 minutes, 360 ppm of propylene in  $\text{N}_2$  for 20 minutes,  $\text{N}_2$  for 10 minutes, and then air for 10 minutes.

The magnitude of sensor response to 360 ppm propylene depends strongly on the operating temperature. A sensor operating temperature of  $100^\circ\text{C}$  is too low for propylene to dissociate on the Pd surface, so the device does not respond at all. The three other curves for  $200^\circ\text{C}$ ,  $300^\circ\text{C}$ , and  $400^\circ\text{C}$  show that elevating the temperature increases the sensor's response to propylene. The presence of propylene can be

detected at any of these higher temperatures with 200°C being the minimum operating temperature determined in this study. Since the standard long-term operating temperature of Si is usually below 200°C, these results demonstrate the significant advantages of using SiC rather than Si in  $C_xH_y$  gas sensing applications.

However, the Pd/SiC sensor response is affected by extended high temperature heating. Prolonged heating at 425°C has been shown to change the sensor properties and to decrease sensor sensitivity. The reason for this change in diode properties is likely due to reactions between the Pd and SiC at the interface upon heating.




Figure 2. The temperature dependence of the zero bias capacitance to various gas mixtures. The response to propylene is seen to be strongly temperature dependent.

Efforts have been underway to stabilize the sensor structure for long-term, high temperature operation. Two new structures have been demonstrated which improve the stability of the Pd-based Schottky diode structure over that of Pd/SiC.<sup>8</sup> These structures involve 1) The use an alloy as the catalytic metal. 2) The use of a MIS structure where the “insulator” stabilizes the structure and is also reactive to the gases of interest. Preliminary testing of both of these structures suggests significantly improved stability and response over Pd/SiC.

## Nitrogen Oxide and Carbon Monoxide Detection

A microfabricated and micromachined Si-based structure with a chemically sensitive resistor is being used to measure  $NO_x$  and CO detection. The Si is used as a platform on which the structure necessary for the sensor is fabricated. This sensor structure, shown in Figure 3, includes a temperature detector, heater, and sensing element. The microfabrication process allows the sensor to be small in size with low heat loss and minimal energy consumption. Energy consumption is further reduced by etching out the backside of the Si wafer so that the sensor components (temperature detector, heater, and sensing element) are over a diaphragm region. This minimizes the thermal mass of the sensing area thereby decreasing power consumption for heating and decreasing the time for thermal equilibrium. The temperature detector and heater are doped into the Si substrate for operation over a wide temperature range. The electrode material is Pt and the sensor dimensions are approximately 300 microns on a side with a height of 250 microns.




Figure 3. The structure of a tin-oxide  $NO_x$  and CO sensor including temperature detector, heater, and sensing element.

The sensing element is composed of interdigitated electrode elements across which is deposited  $SnO_2$ . Changes in conductivity of doped  $SnO_2$  across the interdigitated electrodes is measured and correlated to  $NO_x$ .



concentration. A major component of this development work is to stabilize the  $\text{SnO}_2$  for long-term, high temperature operation. Drift in the properties of  $\text{SnO}_2$  with long term heating due to grain boundary annealing have been previously noted.<sup>9-10</sup> This drift results in changes in the sensor output with time and reduces sensor sensitivity. In order to stabilize the  $\text{SnO}_2$  structure for long term operation, the fabrication of nanocrystalline  $\text{SnO}_2$  is being investigated. Nanocrystalline materials have several inherent advantages over conventionally fabricated materials including increased stability and sensitivity at high temperature.<sup>11-12</sup>

Several prototypes of these devices using nanocrystalline  $\text{SnO}_2$  have been fabricated and evaluated. The sensitivity of the  $\text{SnO}_2$  to  $\text{NO}_2$  at  $360^\circ\text{C}$  is shown in Figure 4. The sensor is shown to be able to detect  $\text{NO}_2$  down to the 5 ppm level. The sensor tends to saturate at higher  $\text{NO}_2$  concentrations but the highest level of sensitivity is in the lower ppm range which is the region of interest. Similar results are seen with the detection of CO.




Figure 4. The response of a tin-oxide sensor to a range of  $\text{NO}_2$  concentrations at  $360^\circ\text{C}$ .

### Oxygen Detection

The development of a microfabricated  $\text{O}_2$  sensor has been initiated for safety purposes in aerospace applications but significant

applications also exist in the area of aeronautics emission control. Commercially available  $\text{O}_2$  sensors are typically electrochemical cells using zirconium dioxide ( $\text{ZrO}_2$ ) as a solid electrolyte and Pt as the anode and cathode.<sup>13</sup> The anode is exposed to a reference gas (usually air) while the cathode is exposed to the gas to be detected. Zirconium dioxide becomes an ionic conductor of  $\text{O}^-$  at temperatures of  $600^\circ\text{C}$  and above. This property of  $\text{ZrO}_2$  to ionically conduct  $\text{O}_2$  means that the electrochemical potential of the cell can be used to measure the ambient oxygen concentration at high temperatures. However, operation of these commercially available sensors in this potentiometric mode limits the range of oxygen detection. Further, the current manufacturing procedure of this sensor is relatively labor intensive and costly resulting in a complete sensor package with a power consumption on the order of several watts.

The objective of this research is to develop a zirconium dioxide solid electrolyte  $\text{O}_2$  sensor using microfabrication and micro-machining techniques. The combination of a fuel with  $\text{O}_2$  produces a hazardous environment. Thus, the measurement of both the fuel and  $\text{O}_2$  simultaneously is useful in leak detection applications. Also, the presence of  $\text{O}_2$  often affects the response of  $\text{H}_2$ ,  $\text{C}_x\text{H}_y$ , and  $\text{NO}_x$  sensors. An accurate measurement of the  $\text{O}_2$  concentration will help quantify the response of other sensors in environments where the  $\text{O}_2$  concentration is varying. Therefore, the combination of an  $\text{O}_2$  sensor with other microfabricated gas sensors is envisioned to optimize the ability to detect leaks and monitor emissions.

A schematic of the sensor design is shown in Figure 5. As discussed in the  $\text{NO}_x$  detection section above, microfabricating the sensor components onto a micromachined diaphragm region allows the sensor to be small in size and have decreased energy consumption and time for thermal equilibrium. When

operated in the amperometric mode, the current of this cell is a linear function of the ambient  $O_2$  concentration. This linear response to oxygen concentration significantly increases the  $O_2$  detection range of the sensor. A chamber structure with a well-defined orifice is micro-machined to cover the sensing area. This orifice provides a pathway to control oxygen diffusion which is important in amperometric measurements. This orifice also protects the integrity of the sensing electrode from impinging particles. Preliminary testing of the complete  $O_2$  sensor has been accomplished and further improvements on the design are planned.




Figure 5. The structure of a microfabricated amperometric oxygen sensor. The dimensions of this sensor are comparable to that of the  $NO_x$  sensor shown in Figure 4.

### CO<sub>2</sub> Detection

The detection of  $CO_2$  is, like the detection of oxygen, based on the use of a solid electrolyte. The significant difference from the  $O_2$  sensor will be the use of NASICON (sodium super ionic conductor) as the solid electrolyte. NASICON is an ionic conductor composed of  $Na_3Zr_2Si_2PO_{12}$  which has previously been shown to be sensitive for  $CO_2$  detection. The preparation of the NASICON will be performed using a sol-gel technique. The sensor structure will be similar to that of Figure 5: a microfabricated, miniaturized sensor structure which can be incorporated with other sensors such as the

$CO$  sensor. A combined  $CO_2/CO$  sensor is of interest not only for fire safety applications but for combustion monitoring applications as well.

### High Temperature Electronic Nose Concept

The successful development of the individual high temperature sensors discussed above will allow the formation a sensor array which will allow the detection of a number of gases on a single chip. For example, the formation of an array of the sensors discussed in this paper will detect  $H_2$ ,  $C_xH_y$ ,  $NO_x$ ,  $CO$ ,  $O_2$  and  $CO_2$ . These gases will be detected using three different platforms: a Schottky diode, a resistor, and an electrochemical cell.

Development of such a micro-fabricated gas sensor array operable at high temperatures and high flow rates would be a dramatic step in allowing the monitoring and control of emissions produced by an aeronautic engine. This gas sensor array would, in effect, be a *high temperature* electronic nose and be able to detect a variety of gases of interest. Several of these arrays could be placed around the exit of the engine exhaust to monitor the emissions produced by the engine. The signals produced by this nose could be used to determine the constituents of the emission stream and this information then used to control those emissions. The microfabrication of these sensors is necessary: a conventional bulky system would add weight to the aircraft and impede the flow gases leaving the engine.

The concept of an electronic nose has been in existence for a number of years.<sup>14</sup> Commercial electronic noses presently exist and there are a number of efforts to develop other electronic noses. However, these electronic noses depend significantly on the use of polymers and other lower temperature materials to detect the gases of interest. These polymers are generally unstable above  $400^\circ C$  and thus would not be appropriate for use in harsh engine

environments. Thus, a separate development effort is necessary for a high temperature electronic nose.

## COMMERCIAL APPLICATIONS

The gas sensors being developed at NASA LeRC and CWRU are meant for aeronautics and aerospace applications but can be used in a variety of commercial applications as well. For example, hydrogen sensors using palladium silver that were initially developed for application on the launch pad of the space shuttle. These sensors can be applied to an automotive application. GenCorp Aerojet Corporation, in conjunction with NASA Marshall Space Flight Center, has developed hardware and software to monitor and control the NASA LeRC/CWRU sensors. The system can be customized to fit the user's needs, e.g., to monitor and display the condition of the tank of a natural gas vehicle. Several of these systems have been purchased for use on the Ford Motor Company assembly line for natural gas vehicles (NGV). This complete system received a 1995 R&D 100 Award as one of the 100 most significant inventions of that year.<sup>5</sup>

Likewise, the high temperature  $H_2$ ,  $C_xH_y$ ,  $NO_x$ , and  $O_2$  sensors are being developed for aeronautical applications but can be applied in commercial applications. For example, the conditions in an aeronautic engine are similar to those of an automotive engine. Thus, sensors that work in aeronautic engine applications may be operable in automotive engine applications. Other possible applications include catalytic reactor monitoring, alarms for high-temperature pressure vessels, and chemical plant processing.

## SUMMARY

The needs of aerospace applications require the development of sensors with capabilities beyond those of commercial sensors. These requirements include operation in harsh environments, high sensitivity, and minimal size weight and power consumption. Sensor technology is being developed to address these requirements using microfabrication and micromachining technology as well as SiC semiconductor technology. Several types of sensors have been described all of which have aeronautic and space applications. Some of the sensor designs are relatively mature while the development of others is ongoing. The combination of these technologies may allow the development of a high temperature electronic nose to provide complex chemical analysis in harsh environments.

Sensors designed for aeronautic and space applications also have significant commercial applications. One example is the use of the hydrogen sensor in automotive applications. This application involved a sensor not completely developed for a space application but with excellent properties for use in the automotive application. Further, given the similarities of aeronautic engine environments to those of automotive engine environments and chemical process monitoring, sensors developed for aeronautic applications also have a wide range of applicability. Although each application is different and the sensor needs to be tailored for that environment, the base technology being developed for aeronautic and space applications can have significant impact on a range of fields.

## REFERENCES

1. Hunter, Gary W.; "A Survey and Analysis of Commercially Available Hydrogen Sensors", NASA Technical Memorandum 105878, November 1992.
2. Hunter, Gary W.; "A Survey and Analysis of Experimental Hydrogen Sensors", NASA Technical Memorandum 106300, October 1992.
3. "Proceedings of the 1995 Workshop on Fire Detection Research", W. L. Grosshandler, Editor, June, 1995, Gaithersburg, MD, NISTIR 5700.
4. Grosshandler, W. L.; "A Review of Measurements and Candidate Signatures for Early Fire Detection," NISTIR 555, Nat. Inst. Of Stand. And Tech., Gaithersburg, MD, January 1995.
5. Hunter, G. W.; Neudeck, P. G.; Chen, L.-Y.; Liu, C. C.; and Wu, Q.H.; Makel, D. B.; and Jansa, E.; "A Hydrogen Leak Detection System for Aerospace and Commercial Applications," 31<sup>st</sup> IAA/ASME/SAE/ASEE Joint Propulsion Conference and Exhibit, San Diego, CA, July 10-12, 1995 Tech. Rep AIAA-95-2645, 1995.
6. Hunter, G. W.; Neudeck, P. G.; Chen, L.-Y.; Makel, D. B, Liu, C. C.; and Wu, Q.H. and "A Hazardous Gas Detection System for Aerospace and Commercial Applications," 34<sup>th</sup> IAA/ASME/SAE/ASEE Joint Propulsion Conference and Exhibit, Cleveland, OH, July 1998, Tech. Rep AIAA-98-3614, 1998.
7. Chen, L.-Y.; Hunter, G. W.; Neudeck, P. G.; Knight, D.; Liu, C. C.; and Wu, Q. H.; "SiC Based Gas Sensors", in Proceedings of the Third International Symposium on Ceramic Sensors, Anderson, H.U.; Liu, M.; and Yamazoe, N., ed., Electrochemical Society Inc., pp. 92-105, 1996.
8. Hunter, G. W.; Neudeck, P. G.; Chen, L.-Y.; Knight, D.; Liu, C. C.; and Wu, Q. H.; "SiC-Based Schottky Diode Gas Sensors", Proceedings of International Conference on SiC and Related Materials, Stockholm, Sweden, Sep. 1-7, 1997.
9. Ogawa, H.; Nishikawa, M.; and Abe, A.; "Hall Measurement Studies and an Electrical Conduction Model of Tin Oxide Ultrafine Particle Films", Journal of Applied Physics, vol. 53, pp. 4448-4455, 1988.
10. Xu, C.; Tamaki, J.; Miura, N.; and Yamazoe, N.; "Grain Size Effects on Gas Sensitivity of Porous SnO<sub>2</sub>-Based Elements, Sensors and Actuators, B, vol. 3, pp. 147-155, 1991.
11. Yoo, D. J.; Tamaki, J.; Park, S. J.; Miura, N.; and Yamazoe, N.; "Effects of Thickness and Calcination Temperature on Tin Dioxide Sol-Derived Thin-Film Sensor", Journal of Electrochemical Society, vol. 142, pp. L105-L107, 1995.
12. Vogel, R.; Hoyer, P.; and Weller, H.; "Quantum-Sized PbS, CdS, Ag<sub>2</sub>S, Sb<sub>2</sub>S<sub>3</sub>, and Bi<sub>2</sub>S<sub>3</sub> Particles as Sensitizers for Various Nanoporous Wide-Bandgap Semiconductors", Journal of Physical Chemistry, vol. 98, pp. 3183-3188, 1994.
13. Logothetis, E. M.; "Automotive Oxygen Sensors", Chemical Sensor Technology, Vol. 3, N. Yamazoe, ed., Kodansha Ltd., pp. 89-104, 1991.
14. Gardner, Julian W.; Bartlett, Philip N.; "A Brief History Of Electronic Noses." Sensors and Actuators, B, 18(1-3), 211-20, 1994.



REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE November 1998		3. REPORT TYPE AND DATES COVERED Technical Memorandum
4. TITLE AND SUBTITLE  Microfabricated Chemical Sensors for Safety and Emission Control Applications			5. FUNDING NUMBERS  WU-523-26-13-00	
6. AUTHOR(S)  G.W. Hunter, P.G. Neudeck, L.-Y. Chen, D. Knight, C.C. Liu and Q.H. Wu				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  National Aeronautics and Space Administration Lewis Research Center Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER  E-11418	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)  National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER  NASA TM-1998-208816	
11. SUPPLEMENTARY NOTES Prepared for the 17th Digital Avionics Systems Conference cosponsored by the American Institute of Aeronautics and Astronautics and the Institute of Electrical and Electronics Engineers, Bellevue, Washington, October 31-November 6, 1998. G.W. Hunter, P.G. Neudeck, and L.-Y. Chen, NASA Lewis Research Center; D. Knight Cortez III Service Corporation, Cleveland, Ohio 44135; C.C. Liu and Q.H. Wu, Case Western Reserve University, Electronics Design Center, Cleveland, Ohio 44106. Responsible person, G.W. Hunter, organization code 5510, (216) 433-6459.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Unclassified - Unlimited Subject Category: 35  This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  Chemical sensor technology is being developed for leak detection, emission monitoring, and fire safety applications. The development of these sensors is based on progress in two types of technology: 1) Micromachining and microfabrication (MEMS-based) technology to fabricate miniaturized sensors. 2) The development of high temperature semiconductors, especially silicon carbide. Using these technologies, sensors to measure hydrogen, hydrocarbons, nitrogen oxides, carbon monoxide, oxygen, and carbon dioxide are being developed. A description is given of each sensor type and its present stage of development. It is concluded that microfabricated sensor technology has significant potential for use in a range of aerospace applications.				
14. SUBJECT TERMS  Gas; Hydrogen; Leak; Fire; Emission; Detection			15. NUMBER OF PAGES 14	
			16. PRICE CODE A03	
17. SECURITY CLASSIFICATION OF REPORT  Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE  Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT  Unclassified	20. LIMITATION OF ABSTRACT	